


K-WOOD



Pamesa's K-Wood offers a semi-rustic wood porcelain at a competitive price. The light distressed look is paired with a modern color palette - warm and cold grays - with gentle variation.



DESERT



GRAFITO



MOKA



NOCE

Colors are intended as a guide only and may vary from actual tile. Please check tile samples before making final selections. See reverse side for product information.

Sizes

Rectified

8 x 48 PAKW--/848

Colors

PAKWDT Desert (Warm Light Grey)

PAKWGO Grafito (Cool Dark Grey)

PAKWMA Moka (Warm Medium Grey)

PAKWNE Noce (Greish Brown)



INSTALLATION INFORMATION

We recommend using a tile leveling system to install this product

Before installing the tile you should:

- Ensure the perfect planarity (flatness) of underlying floor base.
- Always double-check the quality of the tiles.
- When setting, tile should be only slightly staggered so that the ends of the tiles are within 8" or less from the ends of the corresponding staggered tile. (See figures 1 & 2)
- Staggered spacing does not need to be uniform, but should not exceed 8" recommendation.
- A minimum joint of 2 or 3 mm between tiles is recommended.
- It is preferable to use a grouting material that matches the color of the tiles.

As with all inkjet lines, there are many different graphics that are mixed and packed randomly. It is important to pull from multiple boxes during installation, rotate pieces and note the placement of the different images in order to get the proper final blend.




Figure 1




Figure 2

Technical Information

Physical Properties	Norms	Value
Average Bending Strength	10545-04	45,5 N/mm ² (average value)
Breaking Strength	10545-04	Compliant
Water Absorption	10545-03	≤ 0,05
Frost Resistance	10545-12	No Damage
Slip Resistance	DIN51130	R9
Abrasion Resistance	10545-7	PEI 4
Dynamic Coefficient of Friction	DCOF	Wet ≥ 0.42

The Coefficient of Friction is a general guide only. Testing may vary with different production runs and with different testing labs. As noted in the American with Disabilities Act (ADA) the coefficient of friction varies considerably due to facts not under the control of entities such as the manufacturers and distributors. These factors include, but are not limited to, contaminants, slope of terrain, drainage conditions, adjacent surfaces, etc. Suitability for any installation can only be determined by a site examination of all conditions that could affect the slip resistance of the tile being installed. Continual cleaning and maintenance must be performed once the tile has been installed. For more information see our current handout *Americans with Disabilities Act and Slip Resistance of Tile*.